

CHO-SORB® SLEEVE BEAD SOLID CORE FERRITIT

Ferriittirengas

83-10-M12928-1000
SLEEVE BEAD FERRITE 5,2MM


- Kiinteitä ferriittejä kaapeleille ja johtimille
- Laaja valikoima
- Useita eri kokoja



TUOTEKUVAUS


TEKNISET TIEDOT


Impedance @ 100 MHz	74
Impedance @ 25MHz	48
Pituus	10mm
Sisähalkaisija	5,2mm
Ulkohalkaisija	9,5mm



CHO-SORB® - Product Information

Table 1		
TYPICAL PROPERTIES		
Property	Units	83-10-XXXX-1000
Material	---	Nickel Zinc
Initial Permeability @ B = 10 Gauss, μ_i	---	850
Flux Density @ BI @ 10 Oersted	Gauss	2750
Residual Flux Density	Gauss	1200
Loss Factor (tan δ , l)	---	120×10^{-4} @ 1 MHz
Curie Temperature	°C	≈ 130
Volume Resistivity	ohm-cm	10^7
Temperature Coefficient of μ_i (20-70°C)	%/°C	1.0
Recommended Frequency Range	MHz	30-200





CH0-SORB® - Product Information

Table 1

TYPICAL PROPERTIES		
Property	Units	83-10-XXXX-1000
Material	--	Nickel Zinc
Initial Permeability @ B = 10 Gauss, μ_i	--	850
Flux Density @ 10 Oersted	Gauss	2750
Residual Flux Density	Gauss	1200
Loss Factor $\tan \delta$, l	--	120×10^{-4} @ 1 MHz
Curie Temperature	°C	+130
Volume Resistivity	ohm-cm	10^9
Temperature Coefficient of μ_i (20-70°C)	%/°C	1.9
Recommended Frequency Range	MHz	30-200

